



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 6, 2018

Ms. Ann Sawchak
EXPAND SYSTEMS, LLC
771 Shallowford Road, Suite 102
Kennesaw, GA 30144

Reference: Laboratory Test Report
Lab Identification No. 29543
Invoice No. 60693

Dear Ms. Sawchak:

One (1) fabric sample, identified as **3196 – LEENANE – PRETREATED**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results
Vertical Char Lengths

18mm

22mm

19mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





Textiles and Apparel Solutions Centre,
The Warehouse, Brewery Lane,
Leigh, Lancashire, WN7 2RJ, UK
Telephone: +44 (0) 1942 265700
Facsimile: +44 (0) 1942 670 788
www.intertek.com/consumergoods

BS EN 14465:2003 Test Report

Report Ref: LEHTX00935718	Buying Division: NONE GIVEN
Date Received: 01/02/2017	Date Issued: 06/02/2017

Company Name & Address	PREMIER TEXTILES GREEN LANE STOCKPORT SK4 2JR
Contact Name	AMANDA CORK

Order No.:	NONE GIVEN
Description:	56" LEENANE
Colour(s):	NATURAL
Supplier:	NONE GIVEN
End Use:	SOFT FURNISHING
Quoted Composition:	93% COTTON 7% LINEN
Ref/Style/Stroke No.:	NONE GIVEN
Quality:	NONE GIVEN
Batch No.:	NONE GIVEN
Spec. No.:	TABLE 1

Test	Method	Colour	Pass/Fail
ABRASION RESISTANCE (FLAT WOVEN)	BS EN ISO 12947-2/BS EN 14465: 2003 ANNEX A		Pass B

Joanne McGee
(Technician)





Textiles and Apparel Solutions Centre,
 The Warehouse, Brewery Lane,
 Leigh, Lancashire, WN7 2RJ, UK
 Telephone: +44 (0) 1942 265700
 Facsimile: +44 (0) 1942 670 788
 www.intertek.com/consumergoods

Upholstery - Martindale Abrasion (12 kPa Load)		RH 65% +/-4% / Temp 20°C +/-2°C			
Sample	Results				Minimum Requirements
	Change in Shade @ 3,000 Revs = Grade 4-5				
Fabric Type Flat Woven	Head 4: No Fabric Breakdown @ 24,000 revs Fabric Breakdown @ 26,000 revs Heads 1, 2 & 3: No Fabric Breakdown @ 28,000 revs Fabric Breakdown @ 30,000 revs				A = 35,000 revs B = 12,000-30,000 revs C = 4,000-10,000 revs
Overall Result	24,000 revs				
Overall Performance Level	B				
BS 2543: 2004 Classification (Minimum levels for customer reference)					
	LD	GD	HD	GC	SC
Flat Woven	B - 15,000	B - 20,000	B - 25,000	B - 30,000	A - 40,000
Figured Weaves	B - 12,000	B - 15,000	B - 20,000	B - 30,000	A - 40,000
Woven/Flocked/Non-Woven Pile Fabrics	C - 15,000	C - 20,000	B - 25,000	B - 25,000	B - 30,000
Knitted	B - 15,000	B - 20,000	B - 25,000	B - 25,000	B - 30,000





Textiles and Apparel Solutions Centre,
The Warehouse, Brewery Lane,
Leigh, Lancashire, WN7 2RJ, UK
Telephone: +44 (0) 1942 265700
Facsimile: +44 (0) 1942 670 788
www.intertek.com/consumergoods

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

